



Test
TS EN ISO/IEC 17025
AB-0556-T

AB-0556-T

FTST241350

11-24



EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

Dilovası Organize San. Böl. 5.Kısım Fırat Cad.No:18 41455

Dilovası, Kocaeli / TÜRKİYE

DENEY RAPORU

TEST REPORT

Müşterinin adı/adresi <i>Customer name/address</i>	: GENTUĞ TEKSTİL ÜRÜNLERİ SAN. VE TİC.A.Ş. Keresteciler Sit. Savaş. Cad. Söğüt Sok. No:1 Güngören, İstanbul / TÜRKİYE
İstek numarası <i>Order No.</i>	: EEA-24-001288
Numunenin adı ve tarifi <i>Name and identity of test sample</i>	: Arketa - 177,7 kg/ m ³
Numunenin kabul tarihi <i>The date of receipt of sample</i>	: 16.10.2024
Açıklamalar <i>Remarks</i>	:
Deneyin yapıldığı tarih <i>Date of test</i>	: 14.11.2024
Raporun sayfa sayısı <i>Number of pages of the Report</i>	: 4 (6 pages including appendixes)

Deney laboratuvarı olarak faaliyet gösteren Efectis Era Avrasya Test ve Belgelendirme A.Ş., TÜRKAK'tan AB-0556-T ile TS EN ISO/IEC 17025:2017 standardına göre akredite edilmiştir.

Efectis Era Avrasya Test ve Belgelendirme A.Ş. accredited by TÜRKAK under registration number AB-0556-T for EN ISO/IEC 17025:2017 as test laboratory"

Türk Akreditasyon Kurumu (TÜRKAK) deney raporlarının tanınması konusunda Avrupa Akreditasyon Birliği (EA) ve Uluslararası Laboratuvar Akreditasyon Birliği (ILAC) ile karşılıklı tanınma antlaşmasını imzalamıştır.

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports

Deney ve/veya ölçüm sonuçları, genişletilmiş ölçüm belirsizlikleri (olması halinde) ve deney metotları bu sertifikanın tamamlayıcı kısmı olan takip eden sayfalarda verilmiştir.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report

Mühür

Seal



Tarih

Date

27.11.2024

Deney Sorumlusu

Person in charge of test

e-signed

Tuğçe AKOĞLAN

Onaylayan

Approval

e-signed

Ali BAYRAKTAR

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.

İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

TEST REPORT

on Fire and Technical Characteristics

Our ref.: EEA-24-001288

Sponsor: GENTUĞ TEKSTİL ÜRÜNLERİ SAN. VE TİC.A.Ş.
Keresteciler Sit. Savaş. Cad. Söğüt Sok. No:1 Güngören, İstanbul / TÜRKİYE

TEST ITEM

Product name: Arketa - 177,7 kg/ m³

Manufacturing Plant: GENTUĞ TEKSTİL ÜRÜNLERİ SAN. VE TİC.A.Ş.
Organize Sanayi Bölgesi 13. Ada ¼ Parsel, Beykoz Belediyesi, Düzce / TÜRKİYE

Composition: Polyester felt

Appearance: Thickness of the grey polyester felt board is 9 mm and the density is 177,7 kg/m³.

Mounting of the samples: Three polyester felt samples with a width of 590 mm and a length of 2400 mm were placed. No additional support was used.

Date of receipt of the sample: 16.10.2024

Date of realization of tests: 14.11.2024

Sampling: Samples were delivered by the sponsor.

Test Method: ASTM E84 – 23d

Conditioning: ASTM E84 – 23d, clause 6.4 (23 °C ± 2.8 °C) temperature & (50% ± 5%) RH

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

MEASURED VALUES AND THE TEST RESULTS

FSI [m.min]	0,60
FSI [ft.min]	1,97
SDI [%.min]	2,32
Rounded FSI [ft.min]	0
Rounded SDI [%.min]	0

Observation during the test: No specific conditions were observed during the test.

Conclusion:

The product whose test results are given above meets Class A criteria according to ASTM E84 Standard.

The test results relate to the behaviour of the test specimen of a product under the conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product of use. The results of tests are concerned only with the subject of testing.

The protocol shall not be reproduced except in full without the written approval of the testing laboratory.

Brand, type, quality and dimension information of the components, when it is not possible to be verified by the laboratory, are given according to the sponsor's declaration and the responsibility belongs to the sponsor. The test specimens are tested as received from the sponsor (when the laboratory does not carry out sampling).

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürlü raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Classification:

The International Building Code® (IBC), NFPA 101 and NFPA 5000 all describe a set of classification criteria required for interior wall and ceiling finish materials based on FSI and SDI when tested in accordance with ASTM E84 or UL 723.

The classification criteria for all three standard is the same:

Class	Rounded FSI [ft.min]	Rounded SDI [%.min]
A	0-25	0-450
B	26-75	0-450
C	76-200	0-450

Appendix 1:

The graphs of the measured and calculated values

Appendix 2:




The photograph of the samples before the test

The photograph of the samples after the test


- *FSI: Flame spread index*
- *SDI: Smoke developed index*

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürlü raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid



- Photograph of the samples prior to the test:



- Photograph of the samples after the test:

