

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
24008033- Add-RER
04-24

TEST RESULTS

**FLEXIBLE CELLULAR MATERIALS-DETERMINATION OF DENSITY;
ASTM D3574:2017 TEST A(*)**

Performed in the conditioned room (23±2°C-50±10% RH).

	<u>RESULT</u>	<u>REQUIREMENT</u>
Density (g/cm ³)	0,169 g/cm ³	-

COLOUR FASTNESS TO LIGHT; ISO 105 B02:2014

METHOD 3

Cl4000 Fastness Tester. Test was performed according to Exposure Cycle-AI(temperate zone) condition of this standard.

The blue wool 4 was faded up to grey scale 3.
Evaluated with standard blue wool scale.

	<u>RESULT</u>	<u>REQUIREMENT</u>
	4+	-

Total Uncertainty (%)±0.5 grade

Gen. F136-2/04